

TECHNICAL DATA SHEET

RP StoneText

Product name	<ul style="list-style-type: none">RP StoneText															
Overview	<ul style="list-style-type: none">RP StoneText is a stone effect exterior acrylic render with excellent weather resistant properties. RP StoneText is designed to be applied by spray and gives the appearance of "hammer finished granite". RP StoneText is available in a range of attractive shades.															
Characteristics	<div><ul style="list-style-type: none">Comply with regularting conformity: QCVN 16:2017/BXD và TCVN 8652:2012<table><tr><th>Characteristics</th><th>Unit</th><th>Quality announced</th></tr><tr><td>1. Adhesion</td><td>Class</td><td>Class 1</td></tr><tr><td>2. Scrub resistance</td><td>Cycle</td><td>≥ 1200</td></tr><tr><td>3. Shock temperature resistance</td><td>Cycle</td><td>≥ 50</td></tr><tr><td>3. VOC contant</td><td>g/liter</td><td>≤ 50</td></tr></table></div>	Characteristics	Unit	Quality announced	1. Adhesion	Class	Class 1	2. Scrub resistance	Cycle	≥ 1200	3. Shock temperature resistance	Cycle	≥ 50	3. VOC contant	g/liter	≤ 50
Characteristics	Unit	Quality announced														
1. Adhesion	Class	Class 1														
2. Scrub resistance	Cycle	≥ 1200														
3. Shock temperature resistance	Cycle	≥ 50														
3. VOC contant	g/liter	≤ 50														
Area of Use	<ul style="list-style-type: none">Exterior and interior facades of concrete, cement rendering, EIFS finishing system and wood; on buildings such as commercial complexes, hospitals, industrial complexes, commercial office projects and housing developments.															
Property	<ul style="list-style-type: none">RP StoneText is supplied in paste form, formulated from natural stone chippings dispersed in acrylic resin adding special ceramic chip, quazt sand. The combination provides an excellent protective vapour-permeable coating. It has high resistance to atmospheric corrosion as well as to fading.															
Surface Preparation	<ul style="list-style-type: none">Ensure that all dust, dirt and foreign matter is brushed and scraped away. Also ensure that the surface is solid, free from salts, oil, grease and ridges. All cracks, chips, voids and damages should be repaired with filler prior to application of RP Stonetext.															
Priming	<ul style="list-style-type: none">On the cleaned surface apply a coat of Penetrating Primer.															
Application & Cleaning of Tool	<ul style="list-style-type: none">RP StoneText is supplied ready to use in paste form and is applied using a hopper gun. Using relatively high pressure, an even coat is applied to the entire surface at a rate of approx. 2.0kg/m2. The pressure is then reduced and a further coat is applied at a rate of approximately 1.0kg/m2. This can be left as a textured "hammer finish" or lightly knocked down with a trowel to produce a pitted look. The coating is allowed to dry for 24 to 48 hours after which a clear coat of RP StoneText Topcoat is applied.															

- Clean tools and equipment with water after use.

TECHNICAL DATA

Product	• Stone effect exterior coating.
Consumption	• Approximately 2-3kg/m2.
Coat Thickness	• 2mm
Weather Resistance	• Weather resistant and washable.
Colour	• RP StoneText is available in a range of natural shades.
Binder	• Acrylic binders.
Filler Material	• Natural stone chippings/marble.
Additives	• Chemical resistant additives, plasters and adhesion-improving additives.
Durability	• Life expectancy of 10 years depending upon climatic conditions if correctly applied.
Application	• By hopper gun.
Packaging	• 25kg plastic pails.
Storage	• 12 months in original unopened containers.

Recommendation for Application	• UNi-PRO is recommended to use for the best quality
---------------------------------------	--

*** Due to our policy of continuing product improvement Revolution Paint reserves the right to modify these specifications without further notice.

